

# Reliable system – high yields. Bosch Solar Module $\mu$ m-Si plus

**High-yield – easy-to-assemble – reliable.**  
Solar modules from Bosch Solar Energy.



**BOSCH**

## **Our thin-film modules offer impressive features including:**

- ▶ Excellent annual yields for you and your customers, using non-toxic materials
- ▶ Assembly systems that complement one another perfectly and are supplied from a single source thanks to collaborations with major assembly system manufacturers, including Bosch Rexroth
- ▶ Straightforward, solid installation with low assembly outlay through adaptability of recognized standard components
- ▶ Good usage options on e.g. east-facing, west-facing and slightly sloping roofs

## **Warranty conditions:**

- ▶ 5 years product warranty
- ▶ 25-year performance guarantee (90% up to 12 years, 80% up to 25 years)
- ▶ Product certification to IEC 61646 and IEC 61730

Length [x]	Width [y]	Height [z]	Weight	Junction box	Plug connector	Cable [l]
1300	1100	7.1	25	MultiContact	MC4	Plus 600 Minus 1000
x, y, l in mm, -1 / +3 mm; z in mm, $\pm 0.5$ mm; weight in kg $\pm 0.7$						

Thin-film solar module	
<b>Performance classes</b>	<b>100 Wp, 105 Wp, 110 Wp, 115 Wp</b>
<b>Performance sorting</b>	$\pm 2.5$ Wp
<b>Structure</b>	<b>Frameless glass-glass laminate</b> <ul style="list-style-type: none"> <li>▶ Thermally strengthened front glass</li> <li>▶ PVB or EVA foil</li> <li>▶ Thermally strengthened rear glass</li> <li>▶ Junction box with bypass diode</li> <li>▶ IP-Code Junction Box (IP 65)</li> </ul>
<b>Cells</b>	<b>Amorphous and microcrystalline silicon</b> Multi-junction cell


**Electrical characteristics for STC\*\*:**

Designation	Pmpp [Wp]	Vmpp [V]	Impp [A]	Voc [V]	Isc [A]	Voc initial [V]	Isc initial [A]
$\mu$ -Si 115	115	104	1.11	135	1.44	137	1.46
$\mu$ -Si 110	110	102	1.08	133	1.40	135	1.42
$\mu$ -Si 105	105	100	1.05	131	1.37	133	1.39
$\mu$ -Si 100	100	98	1.02	129	1.34	131	1.37
Reduction in module efficiency with decrease in irradiation level from 1000 W/m <sup>2</sup> to 200 W/m <sup>2</sup> (at 25 °C): -0.60% (absolute)							

**Electrical characteristics for NOCT\*:**

Designation	Pmpp [W]	Vmpp [V]	Voc [V]	Isc [A]
$\mu$ -Si 115	88	99	128	1.15
$\mu$ -Si 110	84	97	126	1.12
$\mu$ -Si 105	80	95	124	1.10
$\mu$ -Si 100	76	93	122	1.07
NOCT: Normal Operation Cell Temperature 48.4 °C; Irradiation level 800 W/m <sup>2</sup> , AM 1.5, temperature 20 °C, wind speed 1 m/s, electrical open circuit operation				

**Dimensions\*:**



\* Drawings and diagrams are not to scale. Detailed dimensions and tolerances are available on request.

\*\* Electrical parameters are typical mean values from historical production data. Bosch Solar Thin Film GmbH assumes no liability for the accuracy of this data for future production batches. All data is subject to a measuring tolerance of  $\pm 3$  %.

**Permissible operating and assembly conditions:**

- ▶ Temperature range -40 °C to +85 °C, humidity max. 85% (rh)
- ▶ Upright assembly, laser lines running vertically
- ▶ Mechanical load-bearing capacity tested up to 2400 Pa
- ▶ Transformerless DC-AC converters are not permitted
- ▶ Maximum 1000 V system voltage

**Weak light performance:**

Intensity [W/m <sup>2</sup> ]	Vmpp [%]	Impp [%]
800	-1.0	-19
600	-2.0	-39
400	-3.0	-59
200	-8.0	-80
The electrical data applies for 25 °C and AM 1.5.		

**Thermal characteristics:**

Temperature coefficient Pmpp	-0.25%/K
Temperature coefficient Voc	-0.31%/K
Temperature coefficient Isc	+0.05%/K

**Bosch Solar Thin Film GmbH**  
 Sonnentor 2  
 99098 Erfurt  
 Germany  
 Phone: +49 361 74376-100  
 Fax: +49 361 74376-199  
[sales.se@de.bosch.com](mailto:sales.se@de.bosch.com)  
[www.bosch-solarenergy.com](http://www.bosch-solarenergy.com)